

# Primary Unalloyed Ingot Composition Limits

Beck Aluminum Corporation

Grade:	SI	FE	ZN	GA	V	Other Each:	Other Total:	Aluminum
	(maximum content per element)							
<b>P0202A</b>	0.02%	0.02%	0.02%	0.02%	0.01%	0.01%	0.02%	Remainder
<b>P0303A</b>	0.03%	0.03%	0.03%	0.03%	0.01%	0.01%	0.02%	Remainder
<b>P0404A</b>	0.04%	0.04%	0.03%	0.03%	0.01%	0.01%	0.03%	Remainder
<b>P0506A</b>	0.05%	0.06%	0.03%	0.03%	0.02%	0.02%	0.05%	Remainder
<b>P0610A</b>	0.06%	0.10%	0.03%	0.04%	0.02%	0.02%	0.05%	Remainder
<b>P1020A</b>	0.10%	0.20%	0.03%	0.04%	0.03%	0.03%	0.10%	Remainder
<b>P1535A</b>	0.15%	0.35%	0.03%	0.04%	0.03%	0.03%	0.10%	Remainder

These composition limits are for reference purposes

These composition limits are based on the Registration Record of Aluminum Association Designations and Chemical Composition Limits for Unalloyed Aluminum, Revised February, 1994