

Primary Unalloyed Ingot Composition Limits

Beck Aluminum Corporation

Grade:	SI	FE	ZN	GA	V	Other Each:	Other Total:	Aluminum
	(maximum content per element)							
P0202A	0.02%	0.02%	0.02%	0.02%	0.01%	0.01%	0.02%	Remainder
P0303A	0.03%	0.03%	0.03%	0.03%	0.01%	0.01%	0.02%	Remainder
P0404A	0.04%	0.04%	0.03%	0.03%	0.01%	0.01%	0.03%	Remainder
P0506A	0.05%	0.06%	0.03%	0.03%	0.02%	0.02%	0.05%	Remainder
P0610A	0.06%	0.10%	0.03%	0.04%	0.02%	0.02%	0.05%	Remainder
P1020A	0.10%	0.20%	0.03%	0.04%	0.03%	0.03%	0.10%	Remainder
P1535A	0.15%	0.35%	0.03%	0.04%	0.03%	0.03%	0.10%	Remainder

These composition limits are for reference purposes

These composition limits are based on the Registration Record of Aluminum Association Designations and Chemical Composition Limits for Unalloyed Aluminum, Revised February, 1994